



PRODUCT DATA

No. Document : DC.RD.DF.08
 No. Reference : DELTA-9XX
 Edition : B
 Revise : 0
 Release Date : 24/10/2007
 Page : 1 of 2



HIGH GLOSS SYNTHETIC ENAMEL

CHARACTERISTICS	Special Properties & Advantages	<ul style="list-style-type: none"> • Good quality alkyd resin. • Good gloss finish and weather resistance. • Easy to apply with excellent flow properties. • Resistant to mild to moderately aggressive environment.
	Composition	An alkyd resin and durable pigment.
SPECIFICATION	Code	DELTA 9XX
	Color	See appropriate Color Card.
	Specific Gravity	1.06 ± 0.05 for white, other color will vary.
	Solid Content	50 % ± 1 (by volume) white, other color will vary
	Spreading Rate	10 - 12 m ² /ℓ (at 40 – 50 μ DFT)
APPLICATION	Intended Use	<ul style="list-style-type: none"> • As topcoat in mild to moderately aggressive environments. • Can be used as finish on timber, metal. • Suitable for both interior and exterior use. rubbed down using a suitable abrasive paper and dusted off.
	Surface Preparation	<ul style="list-style-type: none"> • Applied over a suitable primer undercoat. • Surfaces to be painted must be clean, dry and free of dust, dirt and grease. • Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and dusted off. • For all general structural steelwork, piping, ducting etc, apply 2 coats of Delta Zinc Chromate or Delta Metaprime Zinc Chromate. These would be applied after fabrication and/or erection.
	Directions	<ul style="list-style-type: none"> • Stir gently. • Dilute with thinner TH-AK-0305-0001, 10% is using brush and 10-15% for using spray gun. • Apply evenly and generously with a brush or a spray gun.



PRODUCT DATA

No. Document : DC.RD.DF.08
No. Reference : DELTA-9XX
Edition : B
Revise : 0
Release Date : 24/10/2007
Page : 2 of 2



HIGH GLOSS SYNTHETIC ENAMEL

Drying Time

(at 30°C and standard thickness)

- Dust free : 45 – 60 minutes.
- Touch free : 4 – 5 hours.
- Recoating : Min. 8 hours

PACKAGING

Packing

1 kg and 20 kg.

Storage

Store in good ventilated room.

PRECAUTION

Safety

- Avoid contact with eyes and inhalation of mists when using a spray gun.
 - Ensure there is adequate ventilation in the area where the product is being applied.
 - Close container tightly after use and keep out of reach of children.
-